

## MASTIC PENSULABIL

### CARACTERISTICI:

Agent monocomponent pe baza de cauciuc sintetic. Se aplica utilizand o perie/pensula tare. La scurt timp de la aplicare creeaza o pelicula elastica, rezistenta la temperaturi cuprinse intre -25°C si 80°C, rezistent la apa si uleiuri mineral. Protejeaza imbinarile sudate sau lipite impotriva coroziunii. Se poate aplica pe suprafete metalice si de plastic.

### APLICARE:

Suprafata de aplicare trebuie sa fie curata, uscata si degresata. Se aplica utilizand o perie/pensula tare. La 30min de la aplicare este permisa vopsirea sau lacuirea suprafetei.

### DATE TEHNICE:

Continut VOC (compusi organici volatili): 2004/42/IIB(c)(540) 400


Valabilitate: 12 luni

Densitate: 1,2 g/cm<sup>3</sup>

Eficienta: 1,2kg/m<sup>2</sup> cu o grosime a peliculei de 1mm

Culoare: gri/grafit

Ambalaj: Cutii metalice de 1Kg



Curatare




Pensulabil



Temperatura de utilizare > 15°C



Timp de uscare 30 min. la 20°C



A se pastra la loc racoros